KayCyanine

	Color Index | Type	PROPERTIES									INKS						PLASTICS											PAINTS/FORMULATIONS					
											Offset		Gravure		Flexographic		PVC		Polyethylene		Others											
		Density [20°C]: g/cm³	Specific Surface: m²/g	Oil Absorption: g/100g	Bulk Density: g/cm3	Bulk Volume: l/kg	Conductivity: µS/cm	Dry Content: %	Heat Stability: 0C	Ease of Dispersion	Offset Printing	Letterpress	Solvent Inks	Water based Inks	Solvent based	Water based	Soft PVC	Rigig PVC	LdPe	HdPe	PP	PS	ABS/ASA	PC	Polyamid	Rubber/Elastomers	FIBRES	Baking Systems	Aqueous Systems	Acrylic/Isocyanate Systems	Acid-curable Systems	Amine-curable Systems	Air-Drying Systems
Series -**A** **Pigments for PLASTICS**																																
A-601	Blue 15:0 | **α**	1.6	65 + 5%	-	0.4	-	100-250	-	200	**15**	-	-	-	-	-	-	●	●	X	X	X	X	X	X	X	X	X	-	-	-	-	-	-
A-711	Blue 15:1 | **α**	1.6	58 + 5%	-	0.32	-	50-150	-	300	**15**	-	-	-	-	-	-	●	●	●	●	●	●	□	□	●	●	X	-	-	-	-	-	-
A-715	Blue 15:1 | **α**	1.6	64 + 5%	-	0.33	-	50-150	-	305	**<10**	-	-	-	-	-	-	●	●	●	●	●	●	□	□	●	●	X	-	-	-	-	-	-
A-715.F	Blue 15:1 | **α**	1.6	64 + 5%	-	0.33	-	50-150	-	305	**<10**	-	-	-	-	-	-	●	●	●	●	●	●	□	□	●	●	●	-	-	-	-	-	-
A-931	Blue 15:3 | **β**	1.6	65 + 5%	-	0.2	-	>50	-	280	**15**	-	-	-	-	-	-	●	●	●	●	●	●	□	□	●	●	X	-	-	-	-	-	-
A-931.F	Blue 15:3 | **β**	1.6	65 + 5%	-	0.2	-	>50	-	280	**15**	-	-	-	-	-	-	●	●	●	●	●	●	□	□	●	●	●	-	-	-	-	-	-
A-1041	Blue 15:4 | **β**	1.6	77 + 5%	-	0.2	-	50-200	-	300	**15**	-	-	-	-	-	-	●	●	●	●	●	●	□	□	●	●	X	-	-	-	-	-	-
Series -**L:** **Pigments for INKS**																																
L-602	Blue 15:0 | **α**	1.61	66 ± 10%	39	-	-	-	-	-	**-**	●	●	X	●	□	●	-	-	-	-	-	-	-		-	-	-	-	-	-	-	-	-
L-717	Blue 15:1 | **α**	1.61	66 ± 10%	-	-	-	-	-	-	**-**	X	X	●	●	●	●	-	-	-	-	-	-	-		-	-	-	-	-	-	-	-	-
L-1261	Blue 15:6 | **ε**	1.57	60 ± 10%	40	-	-	-	-	-	**-**	●	●	X	●	●	●	-	-	-	-	-	-	-		-	-	-	-	-	-	-	-	-
L-933	Blue 15:3 | **β**	1.62	6.9 ± 10%	34	-	-	-	-	-	-	●	●	●	X	●	X	-	-	-	-	-	-	-		-	-	-	-	-	-	-	-	-
L-934	Blue 15:3 | **β**	1.62	6.9 ± 10%	36	-	-	-	-	-	-	□	□	□	●	□	●	-	-	-	-	-	-	-		-	-	-	-	-	-	-	-	-
L-1042	Blue 15:4 | **β**	1.62	6.9 ± 10%	36	-	-	-	-	-	-	□	□	●	□	●	□	-	-	-	-	-	-	-		-	-	-	-	-	-	-	-	-
Series -**D:** **Pigments for PAINTS**																																
D-716	Blue 15:1 | **α**	1.65	72 + 5%	-	-	4.0	<200	≥ 98.5	300	**-**	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	●	●	●	●	●	●
D-821	Blue 15:2 | **α**	1.67	52 + 5%	-	-	3.1	<200	≥ 98.5	305	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	●	●	●	●	●	●
D-932	Blue 15:3 | **β**	1.61	49	-	-	4.9	<200	≥ 98.5	280	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	●	●	●	●	●	●
D-935	Blue 15:3 | **β**	1.61	49	-	-	4.9	<200	≥ 98.5	280	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	X	●	●	X	X	X
D-1043	Blue 15:4 | **β**	1.61	64	-	-	4.0	<200	≥ 98.5	300.0	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	●	●	●	●	●	●

● =Suitable

□ =Limited Suitability.

X =Not suitable

| KAY PIGMENTS |

- JEEKA Group Company -

www.jeeka.com